

FSKF PERFORATED

FOIL / SCRIM / KRAFT / FOIL

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.0003 inch	7.6 micron
Barrier Coating	Elastomeric Polymer	0.0001 inch	2.5 micron
Kraft	Natural	30 lbs / 3000 ft ²	49 g / m ²
Adhesive	Flame Resistant		
Reinforcing	Tri-directional Fiberglass	2 / inch (MD) 3 / inch (XD)	8 / 100 mm (MD) 12 / 100 mm (XD)
Barrier Coating	Elastomeric Polymer	0.0001 inch	2.5 micron
Foil	Aluminum	0.0003 inch	7.6 micron

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	27 lbs / 1000 ft ²	132 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	> 10 perm (grains/hr ft ² in Hg)	> 574 ng / N's
Bursting Strength	ASTM D774	35 psi	2.5 kg / cm ²
Puncture Resistance	ASTM C1136	45 beach units	1.3 Joules
Tensile Strength	ASTM C1136	45 lbs/inch width (MD) 25 lbs/inch width (XD)	7.9 kN / m (MD) 4.4 kN / m (XD)
Caliper / Thickness	Micrometer	0.009 inch	229 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

FIRE TESTING	
	ASTM E84
	Foil Side
Flame Spread	5
Smoke Developed	10

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%