




ENGINEERING AND TECHNICAL DATA
Genesis® Mark II
November 2004

Construction: Medium weight clear polyethylene wall hose construction reinforced with a translucent integral polyethylene helix



Product Features:

- Ideal for insulation blowing applications
- Handles both positive and negative pressures
- Easy to handle and extremely flexible in both hot and cold working conditions
- Translucent walls offer easy monitoring of material flow
- Resists clogging
- Convoluted interior design creates efficient air flow that aerates insulation materials and increases machine efficiency with regard to coverage and density
- Crush-resistant
- Manufactured with FDA acceptable materials

Applications: Recommended for light bulk material handling applications.

Temperature Range: -40°F to 140°F

Diameter Range (Inches I.D.): 1.50, 2.00, 2.50, 3.00, 3.50, and 4.00 Inch I.D.

Standard Length: 25 & 50 Feet

I.D. Tolerances (Inches): 1.5, 2, and 2.5 Inch: -0.00 to +0.025 Inch
3, 3.5, and 4 Inch: -0.00 to +0.036 Inch

Standard Color: Clear

End Finish: Plain Cut

Markets: •Clean Rooms •Fertilizer Broadcasting •Food Grade •Insulation Blowing •Pharmaceutical
•Shredders



A SCHAUBURG HOSE TECHNOLOGY COMPANY

1510 Armstrong Road, P.O. Box 4275

Warsaw, IN 46581-4275

Telephone 574-267-7909 • Toll Free 800-343-0428 • Fax 800-382-8464

E-mail sales@flexaust.com • www.flexaust.com



ENGINEERING AND TECHNICAL DATA
Genesis® Mark II
 (Page 2)
 November 2004

SIZE INSIDE DIMENSION (INCHES)	APPROXIMATE WEIGHT (LBS./FT.)	MINIMUM CENTERLINE BEND RADIUS (INCHES)	COMPRESSION RATIO	MAXIMUM RECOMMENDED NEGATIVE PRESSURE (IN./HG.)	MAXIMUM RECOMMENDED POSITIVE PRESSURE (PSI)
1.5	.18	2.2	N/A	29	16
2	.23	3.5	N/A	29	14
2.5	.35	4	N/A	14	13.5
3	.42	5	N/A	9	12
3.5	.45	6	N/A	6	11
4	.55	6.25	N/A	4	10

Note: Technical data based on 2 ft. straight lengths of hose @ 72° F.

Disclaimer: The proper use and maintenance of hose and/or duct manufactured by Flexaust is the sole responsibility of the purchaser and ultimate user of the product. This information is presented as a general guide only. The number of variables which can be present in any application make firm recommendations impossible. Adequate testing under actual service conditions is necessary to properly establish suitability. We take pride in the quality of all Flexaust products and we welcome comments and suggestions from our customers.



A **SCHAUBURG** HOSE TECHNOLOGY COMPANY

1510 Armstrong Road, P.O. Box 4275

Warsaw, IN 46581-4275

Telephone 574-267-7909 • Toll Free 800-343-0428 • Fax 800-382-8464

E-mail sales@flexaust.com • www.flexaust.com